

**TABLE 3 - ANIONIC EMULSIFIED ASPHALT**

	RS-2	EA-90	EA-150	EA-300	SS-1	SS-1H
Viscosity, SFS, 25 C, sec.	-----	-----	-----	-----	20-100	20-100
Viscosity, SFS, 50 C, sec.	100-400	50-500	50-500	50-500	-----	-----
Sieve Test, percent, max.	0.10 <sup>b</sup>	0.50	0.50	0.50	0.10 <sup>b</sup>	0.10 <sup>b</sup>
Cement Mixing Test, percent, max.	-----	-----	-----	-----	2.0	2.0
Demulsibility <sup>a</sup> , 35 ml, 0.02 NCaCl <sub>2</sub> , percent, min.	60	-----	-----	-----	-----	-----
Distillation:						
Oil distillate, by volume of emulsion, percent, max.	-----	4	4	7	-----	-----
Residue, percent, min.	63	65	65	70	57	57
Tests on residue from distillation:						
Penetration, 25 C, 100 g, 5 sec.	100-200	90-150	150-300	300 Min.	100-200	40-90
Ductility, 25 C, 5 cm/min., cm.,min.	40	-----	-----	-----	40	40
Solubility in trichloroethylene, percent, min.	97.5	97.5	97.5	97.5	97.5	97.5
Float Test, 60 C, sec., min.	-----	1200	1200	1200	-----	-----

<sup>a</sup>The demulsibility test shall be made within 30 days from date of shipment.

<sup>b</sup>A percentage of 0.30 is acceptable for samples taken at point of use or shipped to the Central Laboratory for testing.